



STANDARD STRAIGHT BAR

BAR SIZE	* LOCATION CATEGORY		
	A	B	C
#4	1'-9"	1'-3"	1'-0"
#5	2'-2"	1'-6"	1'-3"
#6	2'-7"	1'-10"	1'-6"
#7	3'-5"	Does Not Exist	2'-0"
#8	4'-6"		2'-7"
#9	5'-7"		3'-3"
#10	7'-2"		4'-1"
#11	8'-10"		5'-1"

* LOCATION CATEGORY:

A- Bars in horizontal layers in top of pour with 12" or more of concrete below them such as in: footings, pier caps, etc.

B- All bars not in Category A spaced less than 6" apart.

C- All bars not in Category A spaced 6" or more apart.

Note:

- When development length is not specified on the Plans, the above dimensions shall be used. CASE NO.2 - For bars coated with epoxy not in Case No.1.
- These development lengths do not apply when bar is in lightweight concrete or any other strength of concrete.
- These bar laps only apply where the General Notes indicate "Reinforcing Steel Design, $f_y = 60$ ksi."

APPROVAL	
<i>L.S. Fisher</i> DIRECTOR	
OFFICE OF STRUCTURES	
DATE: 2/2/90	
REVISIONS	
SHA	FHWA
11-23-93	.
1-22-01	.
9-20-05	.
11-26-07	.
FHWA APPROVAL	
DATE:	

STATE OF MARYLAND
DEPARTMENT OF TRANSPORTATION
STATE HIGHWAY ADMINISTRATION
OFFICE OF STRUCTURES
DEVELOPMENT LENGTH DIMENSIONS FOR
GRADE 60 REINFORCING STEEL
IN MIX NO.3 (3500 P.S.I.) CONCRETE
EPOXY COATED REINFORCING CASE NO.2



STANDARD NO. M(6.14)-90-214(L)

SHEET 3 OF 3